
FAA's Airport Pavement Test Vehicle – Need, Capability, and Future Research

Presented to: 2014 FAA Worldwide Airport

Technology Transfer Conference

By: Navneet Garg, Ph.D.

Date: August 6, 2014






Aircraft Tire Pressure Trends

- The trend in aircraft industry is to produce aircraft with extended range capability - results in high gross weight and tire pressures.
- ICAO 'X' category limit was 217-psi.
- Boeing 787 and Airbus 350 will have tire pressures close to 250 psi.

Aircraft Tire Pressure Trends

Proposed X Category Limit





Changes to ICAO Tire Pressure Categories

Tire Pressure Category	Previous ICAO Limits psi (MPa), loaded	New ICAO Limits psi (MPa), loaded
W	Unlimited	Unlimited
X	217 (1.50)	254 (1.75)
Y	145 (1.0)	181 (1.25)
Z	72 (.50)	72 (.50)

NEED FOR APTV/HTPTF

- To develop new specifications for P-401 (based on gyratory compactor) and other HMA related projects, R&D has relied mostly on laboratory testing. Full-scale tests are needed so that the performance prediction models for HMA from laboratory tests can be validated/calibrated to the in-situ pavements.
- NAPTF ideal for testing pavement structure as a whole, not for surface layers.

APTV/HTPTF WILL PROVIDE THAT CAPABILITY.

APTV/HVS-A



AIRPORT PAVEMENT TEST VEHICLE

Heavy Vehicle Simulator – Airport Version (HVS-A)

- Wheel loads up to 100,000 lbs.
- Pavement temperatures up to 150°F
- Test speeds 0.17 to 5 mph
- Single and Dual-Wheel configuration.
- Single wheel will be radial aircraft tires size 52x21.0R22
- Dual wheel assembly is designed to accommodate smaller tires (B-737-800)
- Wander Width 6 feet
- FAA Acceptance November 1, 2013




HVS-A Test Pavement



HVS-A Acceptance Test Strips




HVS-A Acceptance Test Strips




PAVEMENT CROSS-SECTION

HVS-A Acceptance Test Strips



HVS-A TS: Response and Traffic Tests

INSTRUMENTATION LAYOUT FOR HVS-A SITE ACCEPTANCE TEST STRIPS



HVS-A ACCEPTANCE TEST STRIPS

Objectives:

 Study the effects of Tire Pressure on performance of HMA layer.

Tests:

- Response Tests.
- Traffic Tests.



HVS-A TS: RESPONSE TESTS


- Tire pressure: 210-psi Test Strip-1
 245-psi Test Strip-2
- Pavement Temperature: 140 deg. F measured at a depth of 1-inch below pavement surface.
- Test Speed: 2-mph
- Wheel loads: 30,000-lbs, 40,000-lbs, 50,000-lbs.

HVS-A TS: TRAFFIC TESTS

- Tire pressure: 210-psi Test Strip-1
 245-psi Test Strip-2
- Pavement Temperature: 140 deg. F measured at a depth of 1-inch below pavement surface.
- Test Speed: 2-mph
- Wheel loads: 61,300-lbs.


HVS-A TS: Wander Pattern

Sequence No.	Track No.	Transverse Wander Position, in
1	-2	16
2	-2	16
3	0	36
4	0	36
5	2	56
6	2	56
7	1	46
8	1	46
9	-1	26
10	-1	26
11	0	36
12	0	36
13	1	46
14	1	46
15	-1	26
16	-1	26
17	0	36
18	0	36



HVS-A TS: Response and Traffic Tests






HVS-A TS: Response and Traffic Tests






HVS-A TS: Response Tests



HVS-A TS: Response Tests



HTPTF-Construction Cycle 1


Objectives:

- Study the effects of Tire Pressure on performance of HMA layer.
- Study the effect of polymer modified binder on HMA layer performance.
- Evaluate the performance of Warm Mix Asphalt under aircraft wheel load.

MATERIAL

TIRE PRESSURE


BINDER TYPE



TOTAL AREA = 102,600 sq. feet (2.36 acres)



HTPTF Cross Sections



Future Research

- "Green" technologies such as Warm Mix Asphalt
- Stone Matrix Asphalt
- Recycled Asphalt Pavement
- Polymer Modified Binders
- Shear failure of HMA
- Performance of HMA overlays on
 - Flexible Pavements
 - Rigid Pavements

Future Research

Use of Additives and Nanoparticles to Improve Performance of Airport Pavement Materials

- Evaluate the use of Additives and Nanoparticles for Improved Performance of Airport Pavement Materials
- Develop Standards/Specifications and Guidelines for Pavement Materials that have been modified with Nanoparticles and other Additives.

